


## PUR-O-RIP LV

### CE-marking in accordance with EN 1504-5



#### Properties:

*PUR-O-RIP LV* is a low-viscous two-component injection resin based on polyurethane, which is employed for the injecting of dry, wet and pressureless water-bearing cracks in concrete and brickwork.

*PUR-O-RIP LV* hardens through reaction of the A and B-component, as well as through reaction with water in the injection area.

*PUR-O-RIP LV* is a special product for brickwork injection (pore and capillary tube backfilling) and for crack injection, especially for injection of hairline cracks.

#### Technical Data:

##### Substance data of components:

##### *Component A*

Consistency	liquid	
Colour	transparent	
Odour	hardly noticeable	
Spec. density (23°C)	approx. 1.01 g/cm <sup>3</sup>	DIN EN ISO 2811-1
Dyn. viscosity (23°C)	approx. 60 mPas	DIN EN ISO 2555

##### *Component B*

Consistency	liquid	
Colour	brown	
Odour	characteristic	
Spec. density (23°C)	approx. 1.21 g/cm <sup>3</sup>	DIN EN ISO 2811-1
Dyn. viscosity (23°C)	approx. 30 mPas	DIN EN ISO 2555

##### Mixture of A- and B-component:

Processing temperature	5 - 30°C	substrate temperature
Mixing ratio A : B	1.67 : 1 (parts by weight) 2 : 1 (parts by volume)	
Viscosity of mixture (23°C)	approx. 40 mPas	DIN EN ISO 2555

##### Reaction data (at 23°C):

String gel time (Pot-life)	approx. 2 h	ASTM D7487
Final curing	7 d	

#### Processing:

Mix components A and B of *PUR-O-RIP LV* in the prescribed proportions in a dry and clean container with the aid of a mixing device until reaching an homogeneous appearance (no streaks). Afterwards the mix is to be pumped.

Indicated injection pump: *CONTRACTOR 1U*

For cleaning of pump and injection devices we recommend the use of *PUR-O-CLEAN* (see specific TDS).

**Safety information:**

*PUR-O-RIP LV* component A and B are classified as hazardous according to Regulation (EC) 1272/2008 (CLP).

It is therefore necessary, before beginning processing, to become familiar with the precautions and safety advice as indicated in the material safety data sheet.

**Packaging:**

Component A	15 kg metal canister 5 kg metal canister
Component B	9 kg metal canister 3 kg metal canister
Combined packaging	1.63 kg combined can

Bigger packaging on request.

**Storage:**

Shelf life at least 12 month in original packaging when stored in dry conditions between 15-25°C, protected from heat, frost and direct sunlight.

After the expiration the use of the product is generally not recommended, unless an approval has been provided by TPH. This approval can only be obtained by the quality assurance department of TPH releasing the material after verification of main properties being within specification.

**Disposal:**

Small quantities of cured product residues can be disposed of as normal domestic waste. Dispose of not cured product components must be effected in accordance with the corresponding local regulations. For further information please refer to the material safety data sheets.

**Test certificates:**

Concrete injection product based on polyurethane for ductile filling of cracks according to EN 1504-5



TPH Bausysteme GmbH  
Nordportbogen 8  
D-22848 Norderstedt

08

GER0513/02

EN 1504-5:2004

PUR-O-RIP LV

Concrete injection product

<b>Adhesion capacity</b>	Concrete (dry): approx. 1.1 N/mm <sup>2</sup> Concrete (slightly moist): approx. 0.9 N/mm <sup>2</sup>
<b>Elongation capacity</b>	> 10 %
<b>Watertightness</b>	D1
<b>Glass transition temperature</b>	- 1°C
<b>Injectability into dry medium</b>	Injectability class: 0.1
<b>Injectability into non dry medium</b>	Injectability class: 0.1
<b>Durability (compatibility with concrete)</b>	No failure by compressive testing Lost deformation work < 20 %
<b>Corrosion behavior</b>	deemed to have no corrosive effect
<b>Release of dangerous substances</b>	NPD

**Legal notice:**

The correct and thus successful application of our products is not subject to our control. A guarantee can be issued for the quality of our products within the framework of our sales and supply conditions, however not for successful processing. All data and specifications in this specification sheet are based on the present state of the art and the right to changes and adaptations for the sake of development remains explicitly reserved. The consumption specifications designated by us can be only average empirical values, where deviations are possible on an individual basis and therefore cannot be excluded by us.

TPH Bausysteme GmbH  
Nordportbogen 8  
D-22848 Norderstedt

Tel.: +49 (0)40 / 52 90 66 78-0  
Fax: +49 (0)40 / 52 90 66 78-78  
e-mail [info@tph-bausysteme.com](mailto:info@tph-bausysteme.com)  
Web [www.tph-bausysteme.com](http://www.tph-bausysteme.com)